Application No.: 09/767,057 Filing Date: January 22, 2001

Page: 2

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Presented) An opaque white film with a thickness of from 10 to 500 µm, wherein the film comprises a single thermoplastic consisting of polyester which has been selected from the group consisting of polyethylene terephthalate, polybutylene terephthalate, polyethylene naphthalate, and mixtures thereof, as a main constituent, barium sulfate, at least one UV stabilizer, at least one flame retardant and at least one optical brightener, said film exhibiting a yellowness index of less than or equal to 45 for 250 micron films and less than or equal to 20 for 50 micron films.

2. (Canceled)

- 3. (Original) The opaque white film as claimed in claim 1, wherein from 0.2 to 40% by weight of barium sulfate based on the weight of the crystallizable thermoplastic, is present in the film and the barium sulfate is fed to the thermoplastic by way of masterbatch technology during film production.
- 4. (Original) The opaque white film as claimed in claim 1, wherein from 10 to 50,000 ppm of optical brightener, based on the weight of the crystallizable thermoplastic, is present in the film and the optical brightener is fed to the thermoplastic by way of masterbatch technology during film production.
- 5. (Original) The opaque white film as claimed in claim 4, wherein the optical brightener has been selected from the group consisting of bisbenzoxazoles, phenylcoumarins and bisstearylbiphenyls.

PROPAT LLC Fax:7043654851

Feb 28 2005 11:01 POL

Application No.: 09/767,057 Filing Date: January 22, 2001

Page: 3

- 6. (Original) The opaque white film as claimed in claim 1, wherein from 0.01 to 5% by weight, based on the weight of the thermoplastic, of UV stabilizer is present as light stabilizer in the film, and the UV stabilizer has been selected from the group consisting of 2-hydroxybenzophenones, 2-hydroxybenzotriazoles, organonickel compounds, salicylic esters, cinnamic ester derivatives, resorcinol monobenzoates, oxanilides, hydroxybenzoic esters, sterically hindered amines and triazines and mixtures of these, and the UV stabilizer is fed to the thermoplastic as a masterbatch during film production.
- 7. (Original) The opaque white film as claimed in claim 1, wherein from 0.5 to 30.0% by weight, based on the weight of the crystallizable thermoplastic, of flame retardant is present in the film, and the flame retardant has been selected from the group consisting of organic phosphorus compounds, and the flame retardant is soluble in the thermoplastic.
- 8. (Original) The opaque white film as claimed in claim 7, wherein the organic phosphorus compound is selected from carboxyphosphinic acids, anhydrides of these and dimethyl methylphosphonate.
- 9. (Original) The opaque white film as claimed in claim 1, wherein from 0.01 to 1.0% by weight of a hydrolysis stabilizer selected from the group consisting of phenolic stabilizers, the alkali metal or alkaline earth metal stearates and the alkali metal or alkaline earth metal carbonates is also present in the film.
- 10. (Original) The opaque white film as claimed in claim 1, wherein a polyestersoluble blue dye selected from the group consisting of cobalt blue, ultramarine blue and anthraquinone dyes, is also present in the film, and the amount of blue dye is from 10 to 10,000 ppm, based on the weight of the crystallizable thermoplastic.

P. 05

Application No.: 09/767,057 Filing Date: January 22, 2001

Page: 4

- 11. (Original) The opaque white film as claimed in claim 1, wherein the barium sulphate is present as precipitated barium sulfate in the film and is in the form of fine-particle colorless powder with an average grain size of from 0.1 to 5 μ m, measured by the Sedigraph method.
- 12. (Previously Presented) The opaque white film as claimed in claim 1, wherein the surface gloss of the film according to DIN 67530 (measurement angle 20°) is greater than or equal to 10, and the luminous transmittance (transparency) of the film, according to ASTM-D 1003 is less than or equal to 30%.
- 13. (Previously Presented) The opaque white film as claimed in claim 1, wherein the film has one or more layers, wherein the film having more than one layer comprises at least one core layer and at least one outer layer.
- 14. (Previously Presented) The opaque white film as claimed in claim 13, wherein, in the film having more than one layer, the barium sulfate, the flame retardant and the optical brightener are present in the core layer, and the UV stabilizer is present in the outer layer(s).
- 15. (Previously Presented) The opaque white film as claimed in claim 14, wherein the outer layers comprise barium sulfate, flame retardant and optical brightener.
- 16. (Previously Presented) The opaque white film as claimed in claim 1, having a scratch-resistant coating, a copolyester or an adhesion promoter on at least one side of the film.
 - 17. (Canceled)
 - 18. (Canceled)

PROPAT LLC

Fax:7043654851

Feb 28 2005 11:02

P. 06

Application No.: 09/767,057 Filing Date: January 22, 2001

Page: 5

19. (Previously Presented) An opaque white film with a thickness of from 10 to 500 µm, wherein the film comprises a crystallizable thermoplastic polyester which has been selected from the group consisting of polyethylene terephthalate, polybutylene terephthalate, and polyethylene naphthalate, barium sulfate, at least one UV stabilizer, at least one flame retardant, at least one optical brightener, and blue dye, said films exhibiting at least a 25 % reduction in yellowness index in comparison to comparable polyester film incorporating either (I) barium sulfate and a stabilized flame retardant or (ii) barium sulfate alone.

20. (Canceled) Please cancel Claim 20.